

**ZINC OXIDE
FRENCH PROCESS**



%

Nodular

325 mesh residue	max.	0.2
200 mesh residue	max.	0.05
900 °C calcination loss	max.	0.5
Water soluble salts	max.	0.1
Matter insoluble in %20 acetic acid	max.	0.1
Humidity	max.	0.1

ZnO	min.	99.5
Fe	max.	0.02
Pb	max.	0.25
Cu	max.	0.0003
Mn	max.	0.0003
Cd	nil	
S	max.	0.1

MEB METAL VE BİLEŞİKLERİ SAN. VE TİC LTD.ŞTİ.

Factory : Baris Mah. Kosuyolu Cad. No: 90 GEBZE/IZMIT TURKEY
Tel : +90 (262) 641 77 10
Fax : +90 (262) 646 53 45
Web : www.mebmetal.com
e-mail : info@mebmetal.com

First Issue : 01.06.1997
Rev. No : 4
Rev. Date : 15.02.2005